


# PARIS

STONE PRODUCT COMPOSITE

## STYLE INFORMATION

|                             |   |
|-----------------------------|---|
| <b>Total Thickness (mm)</b> | 5.5mm   |
| <b>Core Thickness (mm)</b>  | 4mm   |
| <b>Underlayment</b>         | 1.5mm EVA   |
| <b>Wear Layer (mm)</b>      | 0.3mm/12mil   |
| <b>CE Certification</b>     | YES   |
| <b>Utilization Class</b>    |  |
| <b>Coating</b>              | PU Coating  |
| <b>Embossing</b>            | Embossed in Register (EIR)  |
| <b>Bevelled</b>             | Micro - Bevel   |
| <b>Fiberglass</b>           | No  |
| <b>Click</b>                | 2G Drop - Lock System   |

## PACK INFORMATION

|                      |                                     |
|----------------------|-------------------------------------|
| <b>Plank Size</b>    | 148x1220mm (5.83"x 48")             |
| <b>Plank per box</b> | 12                                  |
| <b>Sqm per Box</b>   | 2.1667 m <sup>2</sup> (23.32 sq ft) |

## CERTIFICATE



## TECHNICAL INFORMATION

|                                       |                       |   |
|---------------------------------------|-----------------------|---|
| <b>Density</b>                        | 2000kg/m3             |   |
| <b>Dimensional Stability</b>          | X Direction: 0.05%    | ISO 23999:2008                          |
|                                       | Y Direction: -0.12%   |   |
| <b>Castor Chair Resistance</b>        | No Delamination       | EN425                                   |
| <b>Effect of castor chair</b>         | No visible damage     | ISO 4918:2016                           |
| <b>Residual indentation</b>           | 0.01mm                | ISO 24343-1 :2007                       |
| <b>STC Rating</b>                     | 62                    |   |
| <b>IIC Rating</b>                     | 60                    |   |
| <b>Impact Sound Insulation</b>        | 20 dB                 | ISO 717-2                               |
| <b>Light Fastness</b>                 | ≥6                    | EN 20105-B02                            |
| <b>Slip Resistance</b>                | R10                   | DIN 51130                               |
| <b>Chemical Resistance</b>            | High Resistance       | EN 423                                  |
| <b>Curling after exposure to heat</b> | -0.09mm               | ISO 23999:2008                          |
| <b>Fire Resistance</b>                | Bfl-S1                | EN ISO 9239-1                           |
| <b>Stain Resistance</b>               | Index 0: Not affected | ISO 26987:2008                          |
| <b>Antimicrobial activity</b>         | N/A                   | ASTM G 21-96                            |
| <b>Wear Resistance</b>                | Group T               | EN 660-2                                |
| <b>Watertightness</b>                 | N/A                   | EN13553                                 |
| <b>Water Resistance</b>               | 100%                  |   |
| <b>Burning cigarette test</b>         | No visible change     | EN 1399:1997 Method B                   |
| <b>Migration of Certain Elements</b>  | Not Detected          | "EN71-3:1994 +<br>A 1:2000 + AC: 2002 " |
| <b>CPSIA section 108 - Phthalates</b> | Not Detected          | CPSC-CH- C1001-09.3                     |